



### Classification of Natural Weathering [Type of Panels 2 and 3 – EN 13523-19]

| Panel Identification No & Description  | Start of Exposure | Date of Inspection           | Accumulative Time of Exposure (months) | Exposure Site & Corrosivity Category (EN ISO 12944-2)                             | Orientation of Exposed Panel |
|--|-------------------|------------------------------|--|---|------------------------------|
| 7KK17 – Colorcoat Prisma   | 25/2/2008         | 10/03/2010                   | 24 months                              | Sainte Anne BREST (France)<br>Carbon Steel – C5 (Very High)<br>Zinc – C3 (medium) | 90° North<br>and 5° South    |
| <b>Average Edge Delamination (mm)</b>  |                   | <b>Damage on Bend</b>        |  | <b>Blistering</b>   |                              |
| Conforms to RC5 requirements   |                   | Conforms to RC5 requirements |  | Conforms to RC5 requirements  |                              |
| <b>Corrosion Resistance Category (as defined by EN 10169-2)</b>  |                   |                              |  |   |                              |
| The coil coated material ref <b>7KK17 (Colorcoat Prisma)</b> may be classified RC5 according to standard EN10169-2 |                   |                              |  |   |                              |

Brest, April 1<sup>st</sup>, 2010

Written by Jean-Michel Hamoignon

Approved by Nathalie Le Bozec

Stamp



**Appendix : photographs of the samples after 2 years of exposure**



**CORUS 7KK17B.90N**



**CORUS 7KK17B.5S**